

TECHNICAL SHEET: S-81400

MATTE BLACK TOPCOAT SPRAY

DESCRIPTION AND FIELDS OF APPLICATION

Premium acrylic enamel.

An extreme high content of pigments and specific additives provide excellent opacity, high film-thickness, low tendency for runs and good adhesion direct on steel, galvanised and aluminium.

It can be applied either for spot repairs or refinishing parts.

VOC 661 g/l – 2004/42/EC – IIB (e) (840)

TECHNICAL DATA

Composition:	Thermoplastic acrylic resin
Specific weight:	0,8 kg/l a 20°C
Colour:	Matt black
Safety data:	Refer to the safety sheet
Storage:	12 months, under appropriate storage conditions







CAUTIONS

- Do not apply the product on connected equipment.
- After use, reverse the cylinder and empty the valve.
- If the diffuser jams, replace it with a new one.
- Store in a cool, ventilated place, avoiding direct exposure to sunlight.
- Store between +5°C and +30°C.

TECHNICAL SHEET: S-81400

MATTE BLACK TOPCOAT SPRAY

INSTRUCTIONS FOR USE - APPLICATION

	<p>Shake the aerosol before use at least for 2 minutes after hearing the steel mixing balls move. Carry out test spray. Check the colour.</p>
	<p>20-25 cm</p>
	<p>2-3 coats Dry film thickness: 15-20 μ/coat</p>
	<p>5 min</p>
	<p>20°C: 10-15 min</p>
	<p>20°C: 60 min</p>

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.
