

VETRORESINA PUTTY

DESCRIPTION AND FIELDS OF APPLICATION


Special putty reinforced with fiberglass, appropriate to repair polyester parts and rusted metallic areas. It provides easier mixing, improved creaminess and adhesion to multiple substrates. You don't need to apply an excessive amount of product, avoiding future problems at later stages of the repair process

Voc < 250 g/l according 2004/42CE - 23g/l

TECHNICAL DATA

Composition:	Unsaturated polyester resin, mineral charges and fiberglass
Specific weight:	1,60± 0,05 kg/l
Available colours:	Green
Safety data:	Refer to the safety sheet
Storage:	12 months, under appropriate storage conditions

SURFACE PREPARATION






	<ul style="list-style-type: none"> • TPO, iron, steel plate, glass fiber reinforced plastic • Original paints or aged topcoat finishes. • Clean well the surface to be treated with 6005 Degreaser. Make sure it is dry and free from silicone, wax, grease and any extraneous material. • On base coats or enamel top coats, sand and clean the surface before applying the putty.
---	---

CAUTIONS

<ul style="list-style-type: none"> • Mix well the adhesive with 2-3 % paste hardener. Do not exceed with the hardener to avoid risk of staining during painting operations. • Do not use the product at temperatures below 5°C. • Keep in a cool, dry place.

VETRORESINA PUTTY

PROCESSING

	2-3% paste hardener Pot-life = 5' at 20°C
	Application by putty knife
	20' at 20°C
	5' at 80 cm TMAX 80°C
	P80-P150

TOOLS CLEANING

With nitro or washing thinner before the product hardens.

FURTHER STEPS

Polyester finishing putties

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.