

ALUMINUM PUTTY
Fine aluminum filler

DESCRIPTION AND FIELDS OF APPLICATION


Two-component filler containing high percentage of aluminum powder, which allows to obtain adhesion, hardness, resistance to water, fuels and lubricants. It has good anti-corrosive properties. It is mainly utilized to recover flaws of fusion, to restore and protect metal sheets, for filling imperfections on zinc-plated materials.

The VOC of this product ready-to-use is below 250 g/l, the category limit as defined by EC Directive 2004/42.

TECHNICAL DATA

Composition:	Unsaturated polyester resins, mineral fillers and alluminum filler
Specific weight:	1,80 ± 0,1 kg/l
Available colours:	Aluminium
Safety data:	Refer to the safety sheet
Storage:	12 months, under appropriate storage conditions

SURFACE PREPARATION






	<ul style="list-style-type: none"> • Zinc-plated sheet, aluminium and its alloys, iron, steel plate, plastics. • Original paints or aged topcoat finishes. • Clean well the surface to be treated with 6005 Degreaser. Make sure it is dry and free from silicone, wax, grease and any extraneous material. • On base coats or enamel top coats, sand and clean the surface before applying the putty.
---	--

CAUTIONS

<ul style="list-style-type: none"> • Mix well the adhesive with 1-3 % paste hardener. Do not exceed with the hardener to avoid risk of staining during painting operations. • Do not use the product at temperatures below 5°C. • Keep in a cool, dry place.

ALUMINUM PUTTY
Fine aluminium filler

PROCESSING

	<p>1-3% paste hardener Pot-life = 3-5' at 20°C</p>
	<p>Application by putty knife</p>
	<p>< 30' at 20°C</p>
	<p>4-5' at 1 m.</p>
	<p>P80-P120</p>

TOOLS CLEANING

With nitro or washing thinner

FURTHER STEPS

1K Primer
 Spray Filler
 2K Acrylic Primer

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.