

UHS 2K 2:1 TOP CLEAR
Ultra high solid acrylic clearcoat

DESCRIPTION AND FIELDS OF APPLICATION


2K ultra high-solid acrylic clearcoat for car refinishing.
Easy application, rapid hardening. It allows a quality finish where high gloss and resistance are necessary. It is especially suitable for bodyshop repair work using waterborne base coats, as it cuts effects caused by the absorption of these latter.

The EU VOC limit for this product ready-to-use (product category IIB(d)) is 420 g/l.

TECHNICAL DATA

Composition:	Hydroxylated acrylic resins
Specific weight:	0,991 ± 0,03 kg/l
Available colours:	Colourless, transparent
Safety data:	Refer to the safety sheet

SURFACE PREPARATION








	Matt base coat for two coats of solvent-based paint and water-based paint
---	---

CAUTIONS

- * Two component acrylic paints are affected by moisture
- * Comply with the application ratios
- * Do not use the product at temperatures below 5°C
- * Keep in a cool, dry place

UHS 2K 2:1 TOP CLEAR
Ultra high solid acrylic clearcoat

PROCESSING

	<p>2:1 with 41500-42500 HARDENER Potlife > 45' at 20°C</p>
	<p>19"-20" DIN 4mm at 20°C</p>
	<p>1,2 - 1,4 mm 2,0 - 3,0 bar $\frac{1}{2} + 1 = 50-60$ microns</p>
	<p>1,4 - 1,5 mm. 3,5 - 4,0 bar $\frac{1}{2} + 1 = 50-60$ microns</p>
	<p>10'-15' of evaporation according to temperature</p>
	<p>8h. at 20°C 30' at 60°C</p>
	<p>12' at 1 mt.</p>

TOOLS CLEANING

With thinner for polyurethane products

Technical indications and advices are based on our own experiences.
 We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.