

UHS 2K 2:1 ULTRA RAPID CLEAR COAT

DESCRIPTION AND FIELDS OF APPLICATION


Acrylic UHS ultra rapid Clearcoat. The speed of deep drying allows polishing after just 5 hours at 20 °C. The depth of the final finish provides a superior shine. Easy to apply, thanks to the low viscosity, which remains constant for at least 60 min., it is ideal for both small parts and full car painting. Excellent adhesion on matt bases for two coats of solvent-based and water-based paint. Excellent aging resistance.

The EU VOC limit for this product ready-to-use (product category IIB(d)) is 410 g/l.

TECHNICAL DATA

Composition:	Hydroxylated acrylic resins
Specific weight:	1,0 ± 0,03 kg/l
Colour:	Colourless
Safety data:	Refer to the safety sheet

PREPARACION DEL SOPORTE









	Matt base coat for two coats of solvent-based and water-based paint
---	---

CAUTIONS

- * Acrylic paints are affected by moisture.
- * Comply with the application ratios.
- * Do not use the product at temperatures below 5°C.
- * Keep in a cool, dry place.

UHS 2K 2:1 ULTRA RAPID CLEAR COAT

PROCESSING

	<p>2:1 with 4425-4525-4625 HARDENER Potlife > 60' at 20°C</p>
	<p>18" - 19" DIN 4mm at 20°C</p>
	<p>1,2 - 1,4 mm 2,0 - 2,5 bar ½ + 1 o 2 = 50-60 microns</p>
	<p>1,3 - 1,5 mm 3- 4 bars ½ + 1 o 2 = 50-60 microns</p>
	<p>5'-10' of evaporation according to temperature</p>
	<p> 1h at 20°C  2h at 20°C 10' at 50°C</p>

TOOLS CLEANING

With thinner for polyurethane products

Technical indications and advices are based on our own experiences.
We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.