

TECHNICAL SHEET: S-80400

SILVER WHEELS TOPCOAT SPRAY

DESCRIPTION AND FIELDS OF APPLICATION

Premium acrylic lacquer with good opacity and quick drying.
The professional broad-jet atomization provides an excellent flow and secures a professional result.
It protects the paint against aging.
Ease of application and repainting.

VOC 708 g/l – 2004/42/EC – IIB (e) (840)

TECHNICAL DATA

Composition:	Thermoplastic acrylic resin
Specific weight:	0,7 kg/l at 20°C
Colour:	Aluminium
Safety data:	Refer to the safety sheet
Storage:	12 months, under appropriate storage conditions








CAUTIONS

- Do not apply the product on connected equipment.
- After use, reverse the cylinder and empty the valve.
- If the diffuser jams, replace it with a new one.
- Store in a cool, ventilated place, avoiding direct exposure to sunlight.
- Store between +5°C and +30°C.

TECHNICAL SHEET: S-80400

SILVER WHEELS TOPCOAT SPRAY

INSTRUCTIONS FOR USE - APPLICATION

	<p>Shake the aerosol before use at least for 2 minutes after hearing the steel mixing balls move. Carry out test spray. Check the colour.</p>
	<p>20-25 cm</p>
	<p>2-3 coats Dry film thickness: 10 µ/coat</p>
	<p>2-3 min</p>
	<p>20°C: approx. 10 min</p>
	<p>20°C: 60 min</p>
	<p>in order to increase the degree of gloss and to enhance the fuel resistance, recoat it after approx. 15 min flash-off time (20°C) with 1K clear coat.</p>

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.
