

TECHNICAL SHEET: S-92400

BLACK STONE CHIP PROTECTOR SPRAY

DESCRIPTION AND FIELDS OF APPLICATION

Elastic, noise-reducing and anti-corrosive product.

It protects the vehicles bodies, metal and paint from impact by using its elasticity to absorb the shock and protects from impacting debris. For this reason, it is recommended for treating all the underside parts of the body, plus door-bottoms, wheel-arches etc. Its soundproofing properties make its use advisable inside the bonnet and boot, since it effectively reduces vibration.

Once dry, the excellent texture allows it to be painted with bodywork basecoat paints, achieving a perfect gloss level.

VOC 485 g/l – 2004/42/EC – IIB (e) (840)

TECHNICAL DATA

Composition:	Elastomers and synthetic resins
Specific weight:	1,1 kg/l at 20ºC
Colour:	Black
Safety data:	Refer to the safety sheet
Storage:	12 months, under appropriate storage conditions

CAUTIONS

- Do not apply the product on connected equipment.
- After use, reverse the cylinder and empty the valve.
- If the diffuser jams, replace it with a new one.
- Store in a cool, ventilated place, avoiding direct exposure to sunlight.
- Store between +5°C and +30°C.

www.kmk-refinish.com

36050 Monteviale - Vicenza (Italy) info@kimakem.com



TECHNICAL SHEET: S-92400

BLACK STONE CHIP PROTECTOR SPRAY

INSTRUCTIONS FOR USE - APPLICATION

	Sand and clean the area to be treated. Protect the areas that do not need to be painted. Shake the aerosol before use for 2 minutes after hearing the sound of steel mixing balls. It is also recommended to shake it well during the application process.
	20-30 cm
	2 coats
<u>}</u> †}†	5 min
	20ºC: 10-15 min
	20ºC: 30 min
*	Overpaintable after 1h

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.

Kimakem srl

Via Don G. Fortuna 82 36050 Monteviale – Vicenza (Italy) info@kimakem.com www.kmk-refinish.com